

560515

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 December 2004 (29.12.2004)

PCT

(10) International Publication Number
WO 2004/113230 A1

- (51) International Patent Classification⁷: **C01G 23/047**, C01F 7/14, 7/38, C22B 34/12, 7/00, C01G 49/06
- (21) International Application Number: PCT/GB2004/002543
- (22) International Filing Date: 11 June 2004 (11.06.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 0313886.4 16 June 2003 (16.06.2003) GB
- (71) Applicant (for all designated States except US): **THE UNIVERSITY OF LEEDS** [GB/GB]; Woodhouse Lane, Leeds LS2 9JT (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **JHA, Animesh** [GB/GB]; 30 Sunningdale Avenue, Alwoodley, Leeds LS17 7SE (GB). **MALPAN, Pailo, Antony** [IN/IN]; Scientific Officer (G), Fuel Chemistry Division, IGCAR, Kalpakkam 603 102 (IN). **TATHAVADKAR, Vilas, Dattatray** [IN/IN]; 118 Kasba Peth, Phaltan, MS 415 523 (IN).
- (54) Title: **EXTRACTION PROCESS FOR REACTIVE METAL OXIDES**
- (57) Abstract: The present invention relates to a zero-waste process for extraction of alumina from different types of bauxite ores and red mud residues and of titanium dioxide from ilmenite. Iron oxide is first reduced to metallic iron above the melting point of C-saturated cast iron alloy which yields a high-C iron alloy and an Al and Ti metal oxide rich slag which is then treated with alkali carbonate to form alkali aluminates and titanates. The alkali aluminates are separated by water leaching from which the hydroxide of alumina is precipitated by bubbling CO₂. The residue from water leaching is treated with sulphuric acid and TiO₂ is precipitated via a hydrolysis route. The process recovers most of the metal values and generates only small quantities of silicious residues at pH 4-5 which can be used for soil conditioning. The present also relates to a method for selective separation of TiO₂-rich oxides from titaniferous ore/residue materials via oxidative roasting in the presence of alkali carbonate or carbonates followed by aqueous leaching of the roasted material and selective precipitation of TiO₂ under controlled condition below pH=4.
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2004/113230 A1